

SUNcool

Sputtered aluminum provides a subtle grey appearance with a low visible light reflection and delivers excellent heat rejection.

Total Solar Energy Rejection
 Visible Light Transmission
 Visible Light Reflection
 Visible Light Reflection (Interior)
 Glare Rejection
 Solar Heat Gain Coefficient (SHGC)
 UV Rejection
 IR Rejection

	Total Solar Energy Rejection	Visible Light Transmission	Visible Light Reflection	Visible Light Reflection (Interior)	Glare Rejection	Solar Heat Gain Coefficient (SHGC)	UV Rejection	IR Rejection
Sun Cool 70	31%	68%	9%	10%	25%	0.69	99%	20%
Sun Cool 50	49%	51%	16%	18%	43%	0.51	99%	47%
Sun Cool 40	55%	40%	15%	17%	56%	0.45	99%	60%
Sun Cool 20	70%	22%	24%	25%	76%	0.30	99%	70%



512-246-8468 Austin
 210-490-8468 San Antonio
info@sunsationalsolutions.com
www.sunsationalsolutions.com

Copyright Sunsational Solutions. All Rights Reserved.



SUNSATIONAL SOLUTIONS
 Making Ordinary Glass Extraordinary